

## Muralo Fast Track Waterborne Epoxy Garage Floor Coating M5900

<b>Description:</b>	A durable, long-lasting and easy to maintain, heavy-duty coating specially designed for garage floors. Muralo Fast Track Waterborne Epoxy Garage Floor paint resists "Hot Tire Pick-UP" and automotive fluids and it outperforms ordinary latex and oil/alkyd floor paints.
<b>Recommended Uses:</b>	A specially formulated, high performance, ready to use, acrylic epoxy floor coating designed to seal and protect garage floors. It resists hot tire pick-up and common automotive fluids. It's tough, scuff and mar resistant finish is easy to clean and reduces the need for maintenance.
<b>Surface Preparation:</b>	
Cleaning:	All surfaces to be painted must be in sound condition. Remove loose paint, hard greasy build up and debris by scraping and wire brushing. If possible, remove all previous coatings chemically stripping or a mechanical abraded. Dull all glossy areas by light sanding. Power wash the entire surface with a strong detergent such as TSP or a heavy-duty garage floor cleaner. Flush the surface thoroughly with clean water and allow drying before painting.
Etching:	Allow new poured concrete floors to cure for a minimum of 60 days. All poured or precast concrete surfaces must be acid etched prior to painting. Wear protective clothing, gloves and goggles during etching process. Follow label directions on the container. Rinse the surface thoroughly then neutralize the treated surface with a solution containing ½ pint of household ammonia to a gallon of water. Use a power or pressure washer for a final rinse and wet vacuum the surface to remove the residue left behind from the etching process. Allow the surface to dry thoroughly for 48 hours. Sweep the floor using a stiff bristle broom or a vacuum cleaner to remove remaining residue. For maximum resistance to hot tire pick up, repeat the etching process again over the areas where tires come to rest on the floor. A properly etched surface should look and feel like fine sandpaper. If the surface does not have a proper texture, repeat the etching process.
<b>Application:</b>	Do not thin or add other additives or colorants. Intermix all gallons of the same floor to insure uniformity. Stir thoroughly before use. Roller, brush, pads or sprayer can apply it. Apply generously and evenly with a minimum number of strokes working from unpainted to painted areas. For increased durability and uniform appearance, apply a second coat. Allow paint to dry overnight between coats.  DO NOT APPLY WHEN AIR OR SURFACE TEMPERATURE IS BELOW 50°F
<b>Finish:</b>	Satin
<b>Colors:</b>	M5966 Silver Gray, M5917 Medium Gray
<b>Viscosity:</b>	70-75 KU
<b>Weight Per Gallon:</b>	8.72+/-0.2 pound per gallon
<b>Spreading Rate:</b>	400-450 square feet per gallon over most surfaces. Less on porous surfaces
<b>Solids Content:</b>	33-36 %
<b>Dry Time:</b>	Allow paint to dry 24 hours before walking on the surface. Wait 48 hours before driving on the freshly painted surface. Protect areas under automobile tires with cardboard for two weeks to allow paint to cure completely to prevent lifting of paint

<b>Long-Term Care:</b>	Avoid spilling of automotive fluids, household chemicals and water until paint has dried for at least two weeks. Do not allow spilled liquids to remain on the painted surface for longer periods. Wipe clean spilled areas as soon as possible. If necessary, surface may be washed with soapy water and soft cloth to sponge mop then rinse. Do not use abrasive cleaners or strong detergents.
<b>Thinning:</b>	Not recommended.
<b>Clean Up:</b>	Clean tools immediately with lacquer thinner
<b>Freeze-Thaw:</b>	Passes 3 cycles.
<b>Coating System:</b>	Acrylic Epoxy Resin System
<b>Environmental:</b>	Free of lead, mercury, and heavy metal, non-flammable.
<b>V.O.C. (V.O.S.):</b>	Contains max 400 gms./ltr. Or 3.36 lbs./gal V.O.C.
<b>Formulation:</b>	Pigment* 10-15% Vehicle* 90-85% Acrylic Epoxy Resin Glycols, Ethers, Water, Etc.
<b>Packaging:</b>	Gallons 4/case 37# Quarts 6/case 14#
<b>Caution:</b>	Keep out of reach of children. Avoid prolonged contact with skin or breathing of spray mist. Close container after each use. Do not take internally. Use adequate ventilation. Keep from freezing. Do not apply when temperature is below 50° F.
<b>Architect Specs:</b>	Surfaces noted in the accompanying schedule, after receiving the proper pre-painted treatment described, shall be finished with one or two coats of Muralo Fast Track Waterborne Epoxy Paint. It shall be delivered in the original, unopened cans and applied in accordance with directions furnished by Norton & Son, manufacturers of Muralo Fast Track Waterborne Epoxy Floor Paint and whose directions are made a part of these specifications.
<b>Coverage:</b>	One gallon covers approximately 400 – 450 sq. ft. on smooth surfaces and up to 300 sq. ft. on porous or textured surfaces.
<b>Clean Up:</b>	Clean tools immediately with lacquer thinner
<b>Disposal:</b>	Follow local community waste disposal guidelines.

## **DISCLAIMER**

The information contained herein is presented in good faith. This information is furnished without warranty of any kind. Employers should use this information only as a supplement to other information gathered by them and must make independent determination of suitability and completeness of information from all sources to assure proper use of these Materials and the safety and health of employees. Any use of this data and information must be determined by the user to be in accordance with applicable federal, state and local laws and regulations.

**NOTICE:** Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup.

For additional information, contact the USEPA/Lead information Hotline at 1-800-LEAD-FYI.