

Latex Sand Finish**M0475****Description:**

Muralo Latex Sand Finish is a heavy-bodied Ready Mixed Vinyl Coating for interior use that dramatically covers and refinishes old cracked walls and ceilings and gives an attractive and sturdy appearance to new wallboard and plywood construction.

Recommended Uses:

All rough or smooth painted or unpainted interior surfaces of plaster, wallboard, primed wood or metal, concrete block, brick, stone. It may be tinted with Universal Colorants.

Surface Preparation:

All surfaces must be clean and free from chalk, efflorescence, mildew, dirt, dust, grease, oil and peeling paint. Power scraper or stiff brushes are recommended for masonry surfaces coated with deteriorating paint. Greasy, sooty or dirty surfaces should be washed with detergent and warm water and then rinsed off with clean water. Mildew must be scraped off and then washed down with a solution of 1 cup Clorox and 1 cup T.S.P. to 2 ½ gallons of water. Allow to soak for 30 minutes. Rinse thoroughly before painting.

Efflorescence, white powdery deposits of soluble salts drawn out of masonry by moisture, must be removed before applying Sand Finish. Wire brushing and washing with a weak muriatic acid solution is recommended (1 part acid, 5 parts water). Follow this with a thorough rinsing with clear water.

Glossy surfaces and new wood should be primed with Muralo Latex Enamel Undercoater. Cover exposed nail heads and fill cracks and holes with Muralo Spackle®. Dampen very porous concrete block, brick or stone surfaces. Rust-prone metals and staining woods must be primed with recommended Muralo primers.

Note: Do not apply this product over paper or other wallcovering. If paper or wallcovering has been removed from walls, wash surfaces thoroughly and rinse All paste, glue or starch-bound coatings. Kalsomine or other water-soluble materials must be removed completely before application. Do not apply at temperature below 45°F.

Application:

- Mix thoroughly before using
- Do not thin or mix with other paints. If thinning is needed, add not more than one pint of cold water per gallon
- Use a 4" brush (synthetic bristle) or roller. Many unique designs may also be formed using a sponge, whisk broom, wad of paper, trowel or kitchen spatula.
- Apply about one square yard at a time, completing the pattern in one area before going to the next.
- It can be sprayed with Graco Texture Sprayer Model 225841

Recommended PSI 80
Opening -1/4" (air spray)

Revised 2/2/2004

Clean Up:	Soap and warm water immediately after use																		
Colors:	Available in white only, could be tinted with Muralo Universal Colorants																		
Viscosity:	120-125 KU																		
Weight per Gallon:	13.1 ± 0.2																		
Coverage:	Up to 100 sq. ft. per gallon depending on the type of surface and the depth of texture applied																		
Dry Time:	Varies with the thickness of the coat and with humidity. Under normal drying conditions, it can be recoated the next day if desired.																		
Re-coating:	It can be recoated with alkyd or latex paints without priming.																		
Appearance:	Sand finish																		
Fire Retardant Rating:	N.F.P.A Class "A" when tested on non-combustible substrates																		
V.O.C. (V.O.S.)	Contains max 250 gms/ltr. Or 2.1 lbs/gal V.O.C.																		
Formulation:	<p>475 White</p> <p>Pigment: 59.4%</p> <table border="0"> <tr> <td>Titanium Dioxide</td> <td>5.9%</td> </tr> <tr> <td>Calcium Carbonate</td> <td>49.4</td> </tr> <tr> <td>Silica & Silicates</td> <td><u>44.7</u></td> </tr> <tr> <td></td> <td>100.0%</td> </tr> </table> <p>Vehicle: 40.6%</p> <table border="0"> <tr> <td>Polyvinyl Acetate Copolymer</td> <td>18.6%</td> </tr> <tr> <td>Esters & Glycols</td> <td>3.4</td> </tr> <tr> <td>Volatile (Water)</td> <td><u>78.0</u></td> </tr> <tr> <td></td> <td>100.0%</td> </tr> </table>			Titanium Dioxide	5.9%	Calcium Carbonate	49.4	Silica & Silicates	<u>44.7</u>		100.0%	Polyvinyl Acetate Copolymer	18.6%	Esters & Glycols	3.4	Volatile (Water)	<u>78.0</u>		100.0%
Titanium Dioxide	5.9%																		
Calcium Carbonate	49.4																		
Silica & Silicates	<u>44.7</u>																		
	100.0%																		
Polyvinyl Acetate Copolymer	18.6%																		
Esters & Glycols	3.4																		
Volatile (Water)	<u>78.0</u>																		
	100.0%																		
Packaging:		Per Case	Approx. Weight																
	Gallons	4	52 lbs.																
	2 Gallons	Single	25 lbs.																
	5 Gallons	Single	60 lbs.																
Cautions:	KEEP OUT OF REACH OF CHILDREN. Avoid prolonged contact with skin or breathing of spray mist. Do not take internally. Close container after each use. Use with adequate ventilation. Keep from freezing.																		

DISCLAIMER:

The information contained herein is presented in good faith. This information is furnished without warranty of any kind. Employers should use this information only as a supplement to other information gathered by them and must take independent determination of suitability and completeness of information from all sources to assure proper use of these Materials and the safety and health of employees. Any use of this data and information must be determined by the user to be in accordance with applicable federal, state and local laws and regulations.

NOTICE: Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women.

Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup.

For additional information, contact the USEPA/Lead information Hotline at 1-800-LEAD-FYI.