

Ultra XT Waterborne High Gloss Enamel M1700

Description:

A high gloss tough and durable exterior/interior finish based on Muralo's exclusive X4 acrylic formula. Provides unexcelled adhesion, weather and water resistance, color retention. Goes on smooth and spatter free. Dries fast to a lustrous hard and tack free finish with water clean-up.

Recommended Uses:

Inside and out on practically any surface, including wood, metal, plastic, plaster, wallboard, masonry and canvas.

Surface Preparation:

Clean the surface before painting and make sure it's dry and free of wax, grease, peeling paint, rust and mill scale.

Glossy surfaces should be dulled by sanding or primed with a high adhesion primer such as Muralo Latex Enamel Undercoater.

Ferrous metals should be primed with a good rust preventative such as Muralo Anti-Rust Primer.

New wood should be primed with Muralo Alkyd Primer Sealer.

Application:

Stir before use.

Brush Use synthetic bristled or mixed nylon and bristled brushes

Roller 1/8" mohair roller cover for smooth surfaces and a 1/4 to 1/2 nap for rougher surfaces

Spray May be applied with conventional or airless spray equipment.

Usually an 8 to 10 inch fan at 1 foot distance is ideal for airless and can be obtained with a tip size from .015 to 0.021 inches. For conventional sprayer, usually a 1/4 to 3/16 inch nozzle with an air cap to give a 2-10 inch fan at a distance of one foot.

Temperature of the surface should be at least 50°F when applied

Revised 2/2/2004

Safety Colors:	Safety colors conform to OSHA. Available in yellow, orange, blue, red and green													
Coverage:	Approximately 400 sq ft. per gallon. Covers smooth surfaces with similar colors in one coat. Resistant to rust and corrosion when used over Muralo 1877 to 1878 anti-rust primers													
Dry Time:	Approximately 1 hour. More if humidity is high.													
Federal Spec. Equivalent:	TT-P-1511 Type II													
Fire Retardant Rating:	N.F.P.A. Class "A" when tested on non-combustible substrates													
Formulation:	Pigments= 6.49% Titanium Dioxide 86.45% Color Pigments <u>13.55%</u> 100% Vehicles: 93.51% Acrylic Latex 64.94% Glycols 10.64% Volatile (Water) <u>24.42%</u> 100%													
VOC:	Contains max. 250 gms./ltr. or 2.0 lbs./gal VOC													
Packaging:	<table> <tr> <th></th><th>Per Case</th><th>Approx. Wgt.</th></tr> <tr> <td>Gallons</td><td>2</td><td>25 lbs.</td></tr> <tr> <td>Quarts</td><td>4</td><td>12 lbs.</td></tr> <tr> <td>½ Pints</td><td>6</td><td>25 lbs.</td></tr> </table>		Per Case	Approx. Wgt.	Gallons	2	25 lbs.	Quarts	4	12 lbs.	½ Pints	6	25 lbs.	
	Per Case	Approx. Wgt.												
Gallons	2	25 lbs.												
Quarts	4	12 lbs.												
½ Pints	6	25 lbs.												
Caution:	Keep out of reach of children. Avoid prolonged contact with skin or breathing of spray mist. Close container after each use. Do not take internally. Protect from freezing.													

DISCLAIMER:

The information contained herein is presented in good faith. This information is furnished without warranty of any kind. Employers should use this information only as a supplement to other information gathered by them and must take independent determination of suitability and completeness of information from all sources to assure proper use of these Materials and the safety and health of employees. Any use of this data and information must be determined by the user to be in accordance with applicable federal, state and local laws and regulations.

NOTICE: Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women.

Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup.

For additional information, contact the USEPA/Lead information Hotline at 1-800-LEAD-FYI.