

Muralo Superfinish Interior Latex Eggshell Finish M0400

Description:	A premium quality, spatter-resistant, high hiding, low luster, exceptionally durable interior latex wall and trim finish with the appearance of a flat paint and cleanability of a semi-gloss enamel. The one paint answer to both walls and woodwork, it is ideal for use in children's rooms or play rooms, kitchens, bathrooms, schools, hospitals, office buildings or other institutions where highly scrubbable and durable finish is desired. Muralo Superfinish Eggshell offers all benefits of latex; it's non-yellowing, fast dry, has easy application and water clean up.
Recommended Uses:	Use on all previously painted surfaces, plaster, new and old wood, brick, stone, concrete, cement and cement block and other masonry; wallboard and other drywall construction; and metal.
Surface Preparation:	All surfaces must be clean and free from dirt, dust, grease, oil or peeling paint. A powdery deposit (efflorescence) often found on masonry surfaces should be completely removed with a stiff wire brush. Repair cracks and other imperfections with Spackle [®] . For large holes in plaster, use Muralo Patching Plaster. To repair masonry, use premium quality hydraulic cement.
Recommended Primers:	<p><u>New or Unpainted Surfaces:</u> Prime unsealed or porous surfaces with Muralo Latex Enamel Undercoater #563. Prime new wood with Muralo Alkyd primer sealer #567 to prevent tannin staining. Prime rusting metal with Muralo Rust Inhibitive Primer.</p> <p><u>Previously Painted Surfaces:</u> Previously painted surfaces in sound condition do not require a primer. Use of Muralo Latex Enamel Undercoater #563 is recommended to improve uniformity of the substrate. Dull glossy areas by light sanding to ensure good adhesion.</p> <p><u>Previously Painted: Deep Colors:</u> Cover-All Latex Base Coat tinted to proper color.</p>
Application:	<p>For best results; use:</p> <p>Brush: A good quality synthetic or nylon bristle brush</p> <p>Roller: May be applied with all rollers. Long nap rollers are recommended for rough surfaces and production work.</p> <p>Spray: May be applied with airless or conventional spray equipment. Tip sizes and atomization pressures will vary with the type of equipment used. Usually an 8 to 12 inch fan at 1 foot distance is ideal for airless and can be obtained with a tip size from .015 to .018 inches. For conventional spraying, usually a 0.02 to 0.1 inch nozzle with air cap to give a 4 to 12 inch fan at a distance of one foot, gives excellent results. Follow spray equipment manufacturer's recommendations.</p>
Finish:	Eggshell - 60° Gloss – 5-15°
Colors:	Ready-mixed colors plus white and tint bases
Viscosity:	95 + 10 ku.
Weight per Gallon:	10.00-11.25 lbs. per gallon depending on the color selected.
Coverage:	Covers most surfaces in one coat. Contrasting colors or rough surfaces may require more than one coat.
Spreading Rate:	400-450 Sq. Ft. Per gallon over smooth surfaces. Rough surfaces may reduce the spreading rate.

Solids Content:	33 – 35% by volume															
Recommended Film Thickness:	Wet: Dry:															
Dry Time:	2 – 4 hours at 75° F and 50% relative humidity.															
Thinning:	Not recommended. For spray application or in hot, dry weather, up to ½ pint of water per gallon may be added.															
Clean-up:	Soap and water immediately after use															
Flash Point:	None to Boil.															
Freeze-Thaw:	Avoid Freezing.															
Federal Spec. Equivalent:	TT-P-002119 (Navy-YD) Class II															
Fire Retardant Rating:	N.F.P.A. Class “A” when tested on non-combustible substrates.															
V.O.C. (V.O.S.):	Contains max 150 gms./ltr. Or 1.25 lbs./gal V.O.C.															
Formulation:	Pigment* = 35.2% Titanium Dioxide, Types III, IV.....61.4% Calcium Carbonate.....19.5% Silica and Silicates..... <u>19.1%</u> 100.0% Vehicle* = 64.8% Acrylic Terpolymer Resin.....25.7% Glycols, Esters & Ethers..... 9.7% Additives.....4.3% Water..... <u>60.3%</u> 100.0%															
Packaging:	<table border="0" style="width: 100%;"> <thead> <tr> <th></th> <th colspan="2" style="text-align: center;">Per Case Approx. Wgt.</th> </tr> </thead> <tbody> <tr> <td>5 gals.</td> <td>Single</td> <td>60 lbs.</td> </tr> <tr> <td>2 gals.</td> <td>Single</td> <td>25 lbs.</td> </tr> <tr> <td>Gals.</td> <td>4</td> <td>49 lbs.</td> </tr> <tr> <td>Qts.</td> <td>6</td> <td>20 lbs.</td> </tr> </tbody> </table>		Per Case Approx. Wgt.		5 gals.	Single	60 lbs.	2 gals.	Single	25 lbs.	Gals.	4	49 lbs.	Qts.	6	20 lbs.
	Per Case Approx. Wgt.															
5 gals.	Single	60 lbs.														
2 gals.	Single	25 lbs.														
Gals.	4	49 lbs.														
Qts.	6	20 lbs.														
Cautions:	Keep out of reach of children. Avoid prolonged contact with skin or breathing of spray mist. Close container after each use. Do not take internally. Use adequate ventilation. Keep from freezing. Do not apply when temperature is below 50°F.															

DISCLAIMER

The information contained herein is presented in good faith. This information is furnished without warranty of any kind. Employers should use this information only as a supplement to other information gathered by them and must make independent determination of suitability and completeness of information from all sources to assure proper use of these Materials and the safety and health of employees. Any use of this data and information must be determined by the user to be in accordance with applicable federal, state and local laws and regulations.

NOTICE: Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For additional information, contact the USEPA/Lead information Hotline at 1-800-LEAD-FYI.